

## MAGNEBOND<sup>®</sup> UL-180

---

### Properties

**Magnebond<sup>®</sup> UL-180** has the following characteristics:

- thermal index of 160°C,
- solderable at 390°C without previous removal of the enamel coating,
- very good thermal properties,
- excellent winding properties,
- high resoftening temperature,
- bondable under the action of heat resulting in a bonded coil with similar properties to trickle resin or impregnated coils.

---

### Insulation

**Magnebond<sup>®</sup> UL-180** is a solderable polyurethane enameled copper wire. The final layer is a polyamide aliphatic bondcoat.

---

### Application

**Magnebond<sup>®</sup> UL-180** is designed for the production of self-bonded windings, produced without supporting bobbins and without impregnation, but by either moulding or pressure. It is recommended for windings which need a good compromise between solderability and bonding.

Bonding the coil is rapidly achieved in the production line resulting in higher productivity.

Applications:

- deflection yokes for monitors,
- electrical motors,
- solenoids.

---

### Production range

The standards are:

Diameter:	0.15 to 1.00 mm
Thickness:	Grade 1B and Grade 2B
Color:	Natural

---

### Characteristics

**Magnebond<sup>®</sup> UL-180** fulfills the requirements of the following specifications:

IEC 60317-35  
NEMA MW 3C

---

### Using conditions

The key conditions to be respected are the following :

- bonding temperature between 170 and 200°C, according to the type of aliphatic polyamide bondcoat used (information on request from our technical department)
- accurate quantity of energy applied during bonding process, bonding the coils can be achieved by the joule-effect heating technique.

The values for the intensity and voltage to be applied to the ends of a coil, can be determined as follows :

$$70 M = RI_2t$$

M = mass of wire in grams  
R = resistance in Ohms  
I = intensity in Amperes  
t = length of time in seconds

## MAGNEBOND® UL-180

### MAGNEBOND® UL-180

Valeurs typiques d'un fil <b>Magnebond® UL-180</b> mesurées selon les normes CEI 60 851	Typical values for a <b>Magnebond® UL-180</b> sample according to IEC 60 851 standards	
Diamètre du conducteur Diamètre sur émail Isolation de base Isolation thermo-adhérente	0,50 0,561 Polyuréthane Polyamide aliphatic	Conductor Diameter Overall Diameter Basecoat Bondcoat
<b>Principales caractéristiques</b>		<b>Main characteristics</b>
Indice de température	<b>160°C</b>	Thermal index
Durée de vie de 5000 h à	<b>180°C</b>	5000 h life test
Choc thermique	<b>OK at 200°C</b>	Heat shock
Thermoplasticité	<b>≥ 250°C</b>	Cut through temperature
Tension de claquage	<b>≥ 1,5 x IEC values</b>	Breakdown voltage
Soudabilité	<b>390°C, 4 sec.</b>	Soderability
Flexibilité	<b>10 % + 1 diam.</b>	Flexibility
Allongement	<b>40 %</b>	Elongation
Tangente Delta (isolation de base)	<b>≥ 165°C</b>	Tangente Delta (basecoat)
Température de ramolissement (Méthode CEI 60 851-3/7-1 sur bobinage hélicoïdal)	<b>≥ 160°C</b>	Resoftening Temperature (According to helical coil test IEC 60-851-3/7-1)

Valeurs typiques d'un fil <b>Magnebond® UL-180</b> mesurées selon les normes CEI 60 851	Typical values for a <b>Magnebond® UL-180</b> sample according to IEC 60 851 standards	
Diamètre du conducteur Diamètre sur émail Isolation de base Isolation thermo-adhérente	0,90 0,984 Polyuréthane Polyamide aliphatic	Conductor Diameter Overall Diameter Basecoat Bondcoat
<b>Principales caractéristiques</b>		<b>Main characteristics</b>
Indice de température (isolation de base)	<b>190°C</b>	Thermal index (basecoat)
Durée de vie de 5000 h à (isolation de base)	<b>200°C</b>	5000 h life test (basecoat)
Choc thermique	<b>200°C</b>	Heat shock
Thermoplasticité	<b>≥ 250°C</b>	Cut through temperature
Tension de claquage	<b>≥ 1,5 x IEC values</b>	Breakdown voltage
Soudabilité	<b>390°C, 5 sec.</b>	Soderability
Flexibilité	<b>10 % + 1 diam.</b>	Flexibility
Allongement	<b>42 %</b>	Elongation
Tangente Delta (isolation de base)	<b>≥ 165°C</b>	Tangente Delta (basecoat)
Température de ramolissement (Méthode CEI 60 851-3/7-1 sur bobinage hélicoïdal)	<b>≥ 160°C</b>	Resoftening Temperature (According to helical coil test IEC 60-851-3/7-1)

These values are for information only.

